



## DOBAU<sup>®</sup> - FIX

Accelerating agent for DOBAU<sup>®</sup> - Plast S and DOBAU<sup>®</sup> - 1K

### Uses:

The low viscous accelerating agent DOBAU<sup>®</sup> -FIX is just for shorten the setting time of DOBAU<sup>®</sup> -1K and DOBAU<sup>®</sup> -Plast S.

The usage of DOBAU<sup>®</sup> -FIX makes it possible to apply the one component products even in the cold time of year and at changing weather conditions. The coatings are loadable at an early stage and make shorter construction periods possible. The accelerator is supplied in liquid form and can be stirred well into bitumen emulsions.

### Properties:

DOBAU<sup>®</sup> - FIX distinguishes itself by the following characteristics:

- applicable for DOBAU<sup>®</sup>-1K and DOBAU<sup>®</sup> - Plast S
- clear reduction of the drying times
- easy to dose
- only 1,5 or 2 % addition necessary
- more increased economy by faster working
- faster resistance against rain

### Application instructions:

For the application the bitumen emulsion will be stirred in the tin with a slow running electric stirrer. DOBAU<sup>®</sup> - FIX, which was homogenized before, will be mixed together with the emulsion until it is evenly spread into the compound. Depending on the mixing tool a mixing time of 2-3 minutes is sufficient. The application time is approx.1 hour at a material temperature of 20°C.

### Theoretical material consumption:

Product	trading unit size emulsion	addition DOBAU - FIX
DOBAU <sup>®</sup> - Plast S	25 kg	approx. 0,6 kg
DOBAU <sup>®</sup> - 1 K	28 l	approx. 0,3 kg

### Storage:

Storable in unopened original packages for at least 9 months. The packages have to be stored free from frost and must not be exposed to direct sunshine or excessive warming actions.

### Form of supply:

0,6 kg and 0,3 kg units

### Cleaning agent:

Commercial solvents or petrol; at skin contact hand washing paste

This product information is in accordance with our current information; the stated data are average values under normal conditions. The applicator is obliged to check the suitability and the possible applications for the intended purposes. For special technical information please do not hesitate to contact us. Our products are sold subject to our General Terms and Conditions of Sale.