



DOBAU[®] - SP

Fibre-reinforced filled grouting compound based on bitumen-solvent

Uses:

Grouting compound for the repairing of cracks, joints and hollows etc. as well as for the sealing of chimney and masonry connections, roof aeriels, breakthroughs etc.

Properties:

DOBAU[®] - SP distinguishes itself by the following characteristics:

- it is thinned-ready to use
- resistant against mechanical influences
- fast setting
- no embrittling at cold
- no running out at heat

Application instructions:

Weather conditions:

At the application of DOBAU[®] - SP the air and surface temperatures have to be at least 5°C. Effects by water, rain or frost have to be avoided during the application and drying out time.

Subsoil and application:

The subsoil where DOBAU[®] - SP shall be applied, have to be dry and free from oils, greases and loose particles. Before the application DOBAU[®]-SP has to be completely homogenized by mixing. It can be applied by spatula or smoothing towel. The total layer thickness can be up to 10 mm at each working procedure.

Theoretical material consumption:

For 1 mm dry layer thickness you need approx. 1,3 kg/m² of DOBAU[®] - SP.

Storage:

Storable in unopened original packages for at least 12 months. The packages have to be stored free from frost and must not be exposed to direct sunshine or excessive warming actions.

Form of supply:

5 l and 10 l tins

Cleaning agent:

Commercial solvents or petrol; at skin contact hand washing paste.

Technical data:

Nature:	paste-like
Type of binder:	bitumen
Kind of solvent:	white spirit
Percentage of the solid body (DIN 53 215):	approx. 78 %
Flashing point (DIN 53 213):	approx. 45°C
Softening point of the solid body (DIN 52 011):	approx. 95°C
Heat resistance at 70°C (AIB):	no running out
Cold resistance at 4°C (AIB):	no cracks through banding
Water impermeability (0,2 bar, 8 h AIB):	tight

This product information is in accordance with our current information; the stated data are average values under normal conditions. The applicator is obliged to check the suitability and the possible applications for the intended purposes. For special technical information please do not hesitate to contact us. Our products are sold subject to our General Terms and Conditions of Sale.

Dortmunder Gußasphalt GmbH & Co. KG, Teinenkamp 43, D-59494 Soest, Telephone: +49 (0)2921-8907 0

Fax: +49 (0)2921-8907 70, Internet: www.dga.de, E- mail: info@dga.de

Date: 07/05