



## DOBAU<sup>®</sup> - V

### Thin fluid primer based on bitumen-solvent

#### Uses:

DOBAU<sup>®</sup> - V is a precoat and primer with high penetration of mineral substrates i. e. concrete, masonry or plaster. DOBAU<sup>®</sup> - V is a prime coat for cold and hot applied bitumen based coatings as well as for bituminous roof coverings.

#### Properties:

DOBAU<sup>®</sup> - V distinguishes itself by the following characteristics:

- it fulfils the requirements of DIN 18 195 and AIB DS 835
- it is thinned ready to use
- good bonding to bituminous and mineral surfaces
- resistant against aqueous solvents, thinned acids, salts, lime, cement and others
- fast setting
- dust binding

#### Application instructions:

##### Weather conditions:

During the application of DOBAU<sup>®</sup> - V the air and surface temperatures must be at least 5°C. Effects of water, rain or frost have to be avoided during the application and drying out time.

##### Substrate and application:

The substrate where DOBAU<sup>®</sup> - V is to be applied, must be dry and free from oils, greases and loose particles. Before application DOBAU<sup>®</sup> - V needs to be completely homogenized by mixing. It can be applied by brush or spraying.

##### Theoretical material consumption:

Approx. 0.2 – 0.3 kg/m<sup>2</sup>, depending on the substrate.

##### Storage:

Storable in unopened original packages for at least 12 months. The packages must be stored free from frost and must not be exposed to direct sunshine or excessive heat. The regulation for flammable liquids (VbF) is valid.

##### Form of supply:

5 l, 10 l and 30 l tins

##### Cleaning agent:

In set state: commercial solvents or petrol; at skin contact hand washing paste.

##### Technical data:

Type of binder:	bitumen
Solvent:	white spirit
Nature:	thin flowing
Flash point (DIN 53 213):	approx. 30°C
Density (DIN 52 004):	approx. 0.84 g/cm <sup>3</sup>
<b>Warning:</b>	<b>R 10 flammable</b>

This product information is in accordance with our current information; the stated data are average values under normal conditions. The applicator is obliged to check the suitability and the possible applications for the intended purposes. For special technical information please do not hesitate to contact us. Our products are sold subject to our General Terms and Conditions of Sale.

**Dortmunder Gußasphalt GmbH & Co. KG**, Am Hafenbahnhof 10, D-44147 Dortmund,  
Telefon: +49 (0)231/395797-0, Fax: +49 (0)231/395797-71, Internet: www.dga.de, E-mail: info@dga.de Stand: 08/16