



BIGUMA[®]-BAB 20

Bituminous rail sealing compound in accordance with TL bitFug 82

Uses:

BIGUMA[®]-BAB 20 is a bituminous, polymer modified rail sealing compound in accordance with TLbit Fug 82 for the filling of joints between rails and adjoining surfaces as paving, concrete or asphalt.

Properties:

BIGUMA[®]-BAB 20 fulfils the requirements of "the Technical Delivery Conditions for bituminous joint sealants" (TLbitFug 82), of "rail sealants".

BIGUMA[®] - BAB 20 distinguish itself by the following characteristics:

- plastic elastic set, therefore optimum balance between high movement accommodation and stress relief within the joint
- good application characteristics at heat and at cold
- good bonding at rail and adjoining surfaces
- high ageing resistance of the joint
- resistant against aqueous solutions, salts and thinned acids, or similar
- bituminous building material and therefore problem-free recyclable

Application instructions:

a) Melting:

BIGUMA[®] - BAB 20 has to be heated carefully to the application temperature of 160 - 180 °C in a boiler equipped with mechanical agitation, indirect heating and thermometer. The temperature of the sealant must be thermostatically regulated; it must be controllable at all times. Overheating of the sealant should necessarily be avoided, as this will damage the polymers, which were added for the improvement of the product, and consequently it will lead to a loss of the guaranteed properties.

b) Requirements to the subsoil:

The rail joints to be sealed should be thoroughly blown with high-pressure-air or cleaned with a brushing machine, whereas you have to pay attention to special separation of cleaning and application works. For artificial dry-out or pre-heating of the joints, hot compressed air lances can be used. The rail flanks have to be prepared by removing loose rust particles with the help of sand blasting or equivalent.

For BIGUMA[®]-BAB 20 the primer COLZUMIX[®]-Haftgrund has to be used, which is adapted to this material. The function of the primer is to bind the dust and to form an adhesive layer which will fuse with the sealant being filled into the joints. At the same time the primer also forms a rust protection for the pre-treated rail. The primer must cover the joint flanks completely by forming a film. Before filling the joints the applied primer must have dried, i. e. the surface must be touch-dry.

c) Filling of the joints:

The joint sealant can be applied by can or mechanical by the help of an application lance. The joint sealant must have reached the indicated application temperature during pouring work. If the pouring temperature is clearly below the stated temperature, the flow ability of the sealant suffers. The joint sealants may possibly not fill the to be poured joints completely. There is the danger that voids may occur which later can result in sinking of the sealant under rolling traffic.

To prevent a sinking of the rail joint compound the cell filling has always to be stable.

The cooling of the sealant may cause shrinkage dependent on the joint dimensions; a second pouring can be necessary. This second pouring should be made immediately after the first one.

The joint sealant has to be built-in at least 3 mm deeper of the upper edge of the head of the rail.

Weather conditions:

The prepared joints are only allowed to be sealed at dry weather conditions and at a surface temperature of the building part of 0°C.



Material consumption:

BIGUMA®-BAB 20: joint length (cm) x joint width (cm) x joint depth (cm) x specific gravity of the sealant (g/cm³) = consumption (g).

Primer: The consumption of the primer (COLZUMIX®-Haftgrund) is approx. 3 % of the sealant amount needed.

Storage:

The product has to be stored cold and dry and is storable for at least 24 months

Form of supply:

The joint sealant will be filled into thin metal tins (hobbocks) and transported on non returnable pallets. A separation agent coating and the welded type of the hobbocks guarantee a fast, problem-free and safe removal of the mass out of the tin. The removed blocks can be filled into the heater together with the probably still adherent separation agent coating. Alternatively the joint sealant is supplied in cartons covered with silicone coating.

Metal tin: 33 kg, 12 kg

Carton: 30 kg, 12 kg

Cleaning agent:

Equipment: petrol or commercial solvent

At skin contact: hand washing paste

Authoritative regulations:

At the production or the filling of the joints you have to follow among others the following regulations:

- ZTV Fug-StB 01
- Data sheet on tracks in public traffic areas, which are rolled by traffic

Technical Data:

Application temperature: approx. 160 – 180 °C

Density: approx. 1,38 g/cm³

Primer: COLZUMIX®-Haftgrund

This product information is in accordance with our current information stand, the stated data are average values under normal conditions. The applicator is obliged to check the suitability and the possible applications for the intended purposes. For special technical information please do not hesitate to contact us. Our products are sold subject to our General Terms and Conditions of Sale.