

BIGUMA[®]-TL 82



Polymer modified bituminous joint sealant in accordance with TL Fug-StB and DIN EN 14188-1, Type N2

Uses

The joint sealant is suitable for the sealing of joints in concrete and asphalt pavements.

Properties

BIGUMA[®]-TL 82 fulfils the requirements of "the Technical Delivery Conditions for bituminous joint sealants" (TL Fug-StB 15) and DIN EN 14188-1, Type N2.

BIGUMA[®]-TL 82 or the produced joints distinguish itself by the following characteristics:

- plastic elastic set, therefore optimum balance between high movement accommodation and stress relief within the joint
- designed for a possible change in the joint width of up to 25 %
- good application characteristics at heat and cold temperatures
- good bonding of the bituminous and mineral subsoil
- high ageing resistance of the joint
- resistant against aqueous solutions, salts and thinned acids, or similar
- bituminous building material and therefore problem-free recyclable

Application instructions

a) Melting

BIGUMA[®]-TL 82 has to be heated carefully to the application temperature of 160 - 180 °C in a boiler equipped with mechanical agitation, indirect heating and thermometer. The temperature of the sealant must be thermostatically regulated; it must be controllable at all times. Overheating of the sealant should necessarily be avoided, as this will damage the polymers, which were added for the improvement of the product, and consequently it will lead to a loss of the guaranteed properties.

b) Requirements to the subsoil

The concrete and asphalt joints to be sealed should be thoroughly blown with high-pressure-air or cleaned with a brushing machine if necessary, cleaning and application works have to take place separately. For artificial drying or pre-heating of the joints, hot compressed air lances can be used. For BIGUMA[®]- TL 82 COLZUMIX[®]-Haftgrund primer has to be used, which is especially designed for this material. The function of the primer is to bind any dust bonding to the concrete or asphalt and to form an adhesive layer, which will fuse with the sealant being filled into the joints.

The primer must cover the joint flanks completely by forming a film. It is recommended to prime a stripe of approx. 1 cm width on the pavement at both sides of the joint. Before filling the joints the applied primer must have dried, i. e. the surface must be touch-dry. The primed joint has to dry and be free from dust to guarantee a strong bond to the concrete or the asphalt.

Central Sales

Dortmunder Gußasphalt GmbH & Co. KG

✉ Am Hafenbahnhof 10
44147 Dortmund
Germany

☎ +49 231 395797 - 37
@ info@dga.de

Producer

Dortmunder Gußasphalt GmbH & Co. KG
– A company of the dga-group

c) Filling of the joints

BIGUMA®- TL 82 can be applied by can or mechanical by the help of an application lance. The joint sealant must have reached the indicated application temperature during pouring work. If the pouring temperature is clearly below the stated temperature, the flow ability of the sealant suffers. The joint sealants may possibly not fill the to be poured joints completely. There is the danger that voids may occur which later can result in sinking of the sealant under rolling traffic. Before the application of BIGUMA®- TL 82 a suitable bedding material has to be applied. Through the bedding material the height of the joint sealant in the joint will be modulated. The bedding material should be set firmly at the base of the joint. At the same time a leaking of the compound into possibly existing voids and the three-flank bonding will be prevented. A three-flank bonding may lead to a failure of the joint sealant caused by the tension.

The cooling of the sealant may cause shrinkage dependent on the joint dimensions; a second pouring can be necessary. This second pouring should be made immediately after the first one. The material has to be poured under flushing.

Weather conditions

The prepared joints are only allowed to be sealed in dry weather conditions and at a surface temperature of at least 0°C.

Material consumption

BIGUMA®-TL 82: $\text{joint length (cm) x joint width (cm) x joint depth (cm) x specific gravity of the sealant (g/cm}^3\text{) = consumption (g)}$.

Primer: The consumption of the primer (COLZUMIX® -Haftgrund) is approx. 3 % of the sealant amount needed.

Storage

The product has to be stored cold and dry and is storable for at least 24 months.

Form of supply

The joint sealant will be filled into thin metal tins (hobbocks) and transported on non returnable pallets. A separation agent coating and the welded type of the hobbocks guarantee a fast, problem-free and safe removal of the mass out of the tin. The removed blocks can be filled into the heater together with the probably still adherent separation agent coating.

Cartons: 25 kg, 10 kg

Thin metal tins: 30 kg, 10 kg

Cleaning agent

Equipment: petrol and commercial solvents

At skin contact: hand washing paste

Authoritative regulations

At the production or the filling of the joints you have to follow among others the following regulations:

- ZTV Fug-StB
- ZTV Beton-StB
- ZTV BEA-StB

Central Sales

Dortmunder Gußasphalt GmbH & Co. KG

✉ Am Hafenbahnhof 10 ☎ +49 231 395797 - 37

44147 Dortmund @ info@dga.de

Germany

Producer

Dortmunder Gußasphalt GmbH & Co. KG

– A company of the dga-group

Technical data

Application temperature:	approx. 160 - 180 °C
Density:	approx. 1,1 g/cm ³
Primer:	COLZUMIX®-Haftgrund

Safety information

Please observe the safety data sheet, this contains important information on the handling, transport and storage of BIGUMA®-TL 82.

This product information corresponds to our latest available information. The processor is obliged to test the suitability and application options for the intended purpose. We shall be pleased to advise if you have any questions about our product. Our Terms and Conditions of Business apply, which can be found at www.dga.de.

Rev.: 01/18

Central Sales

Dortmunder Gußasphalt GmbH & Co. KG

✉ Am Hafenbahnhof 10
44147 Dortmund
Germany

☎ +49 231 395797 - 37
@ info@dga.de

Producer

Dortmunder Gußasphalt GmbH & Co. KG
– A company of the dga-group